

Material R values as per AS/NZ 4859.1

Expanded Polystyrene Class "S" AS 13663-1992		
Material Thickness mm	W/mK at 23°C	R value
25	0.0394	R 0.634
38	0.0394	R 0.963
50	0.0394	R 1.268
65	0.0394	R 1.648
75	0.0394	R 1.902
100	0.0394	R 2.530



For more detailed information
scan the QR code to take you
to our website: www.koolfoam.com.au

